

Tefzel™ ETFE 200

Fluoroplastic Resin

Product Information

Description

Tefzel™ ETFE 200 is a general-purpose fluoroplastic resin available in translucent, 2.5-mm (0.1-in.) pellets. Compared to other grades of Tefzel™, its most unique features are an intermediate flow rate and a balance of properties that make it suitable for a variety of processes and demanding end uses.

Tefzel™ ETFE 200 and the other Tefzel™ fluoroplastics are melt processible, modified copolymers of ethylene and tetrafluoroethylene. They are high-performance resins that can be processed at relatively high rates, compared to fluorocarbon resins. They are mechanically tough and offer an excellent balance of properties. Tefzel™ ETFE 200 can perform successfully in applications where other thermoplastics are lacking in mechanical toughness, broad thermal capability, ability to meet difficult environmental conditions, or limited by fabricating problems.

Properly processed products made from virgin Tefzel™ ETFE 200 are inert to most solvents and chemicals, hydrolytically stable, and weather-resistant. Recommended upper service temperature is 150 °C (302 °F); useful properties are retained at cryogenic ranges. The level and stability of dielectric properties are excellent, and the flame rating is V-0 by the UL94 method. Mechanical properties include outstanding impact strength, cut-through, and abrasion resistance. High energy radiation resistance meets IEEE 383, and the resin is approved for nuclear power plant use.

Statements, or data, regarding behavior in a flame situation are not intended to reflect hazards presented by this or any other material when under actual fire conditions.

Processing

Tefzel™ ETFE 200 can be processed by conventional, melt-extrusion techniques and injection, compression, transfer, and blow molding processes. Compared to other grades of

Tefzel™, Tefzel™ ETFE 200 provides intermediate processing rates. Also, the melt viscosity of all grades of Tefzel™ is reduced with increasing shear rate; thus, permitting the use of pressure extrusions through narrow dies without requiring appreciable draw-down. Reciprocating screw injection molding machines are preferred. Corrosion-resistant metals should be used in contact with molten resin. Extruder barrels should be long, relative to diameter, to provide residence time for heating the resin to approximately 345 °C (650 °F).

Typical End Products

Tefzel™ ETFE 200 is ideal for many end products, including electrical components, such as sleeving, coil forms, sockets, connectors, and switches; lab ware, such as tubing, valves, containers, and dishes; battery or instrument components that require chemical inertness; chemical service items, such as valve components, seal glands, pipe plugs, and corrugated tubing; and film.

Safety Precautions

Before using Tefzel™ ETFE 200 resin, refer to the Safety Data Sheet and the latest edition of "The Guide to the Safe Handling of Fluoropolymer Resins," published by The Society of the Plastics Industry, Inc. (www.fluoropolymers.org) or by PlasticsEurope (www.plasticseurope.org).

Open and use containers only in well-ventilated areas using local exhaust ventilation (LEV). Vapors and fumes liberated during hot processing, or from smoking tobacco or cigarettes contaminated with Tefzel™ ETFE 200, may cause flu-like symptoms (chills, fever, sore throat) that may not occur until several hours after exposure and typically pass within about 24 hr. Vapors and fumes liberated during hot processing should be exhausted completely from the work area; contamination of tobacco with polymers should be avoided.

Mixtures with some finely divided metals, such as magnesium or aluminum, can be flammable or explosive under some conditions.

Storage and Handling

The properties of Tefzel™ ETFE 200 resins are not affected by storage time. Ambient storage conditions should be designed to avoid airborne contamination and the formation of water condensation on the resin when it is removed from containers.

Packaging

Tefzel™ fluoroplastic resins are packaged in 20.3-kg (45-lb) plastic bags.

Table 1. Typical Property Data for Tefzel™ ETFE 200 Fluoroplastic Resin

| Property | Test Method* | Unit | Value |
|---|--------------|---------------------|---|
| Thermal | | | |
| Nominal Melting Point | D3159 | °C (°F) | 255–280 (491–536) |
| Flow Rate | D3159 | g/10 min | 7 |
| Upper Service Temperature | UL746 | °C (°F) | 150 (302) |
| Mechanical | | | |
| Tensile Strength, 23 °C (73 °F) | D3159 | MPa (psi) | 45 (6,500) |
| Specific Gravity | D792 | — | 1.7 |
| Ultimate Elongation, 23 °C (73 °F) | D3159 | % | 300 |
| Flexural Modulus, 23 °C (73 °F) | D790 | MPa (psi) | 1,200 (170,000) |
| Impact Strength, 23 °C (73 °F) | D256 | J/m (ft-lb/in) | No Break |
| Hardness Durometer | D2240 | Shore D | 67 |
| Compressive Strength | D695 | MPa (psi) | 38 (5,500) |
| Linear Coefficient of Expansion, 0–100 °C (32–212 °F) | E 831 | mm/mm/°C (in/in/°F) | 13.1 x 10 ⁻⁵ (7.3 x 10 ⁻⁵) |
| Electrical | | | |
| Dielectric Strength, 0.25 mm (0.010 in) | D149 | kV/mm (V/0.001 in) | 70 (1,800) |
| Dielectric Constant, 1 MHz, 23 °C (73 °F) | D1531 | — | 2.5–2.6 |
| Dissipation Factor, 1 MHz, 23 °C (73 °F) | D1531 | — | 0.008 |
| Volume Resistivity | D257 | ohm·m (ohm·cm) | 1 x 10 ¹⁵ (1 x 10 ¹⁷) |
| Arc Resistance | D495 | seconds | 122 |
| General | | | |
| Water Absorption, 24 h | D570 | % | 0.007 |
| Weather and Chemical Resistance | — | — | Excellent |
| Limiting Oxygen Index | D2863 | % | 30–32 |

*ASTM method, unless otherwise specified

Typical properties are not suitable for specification purposes.

Tefzel™ ETFE 200 meets the requirements of ASTM D3159 Type I, Grade 1.

HOW TO USE THE TEFLON™ BRAND NAME WITH YOUR PRODUCT

Tefzel™ is a registered trademark of Chemours for its brand of ETFE fluoroplastic resins. The Tefzel™ brand name is licensed by Chemours in association with approved applications. Without a trademark license, customers may not identify their product with the Tefzel™ brand name as Chemours does not sell such offerings with the Tefzel™ trademark. Unlicensed customers may refer to the Chemours product offering with only the Chemours name and product code number descriptor as Chemours sells its product offerings. There are no fair use rights or exhaustion of rights to use the Tefzel™ trademark from buying from Chemours, a Chemours customer or a distributor without a trademark license from Chemours.

If you are interested in applying for a trademark licensing agreement for the Tefzel™ brand, please visit teflon.com/license

CAUTION: Do not use Chemours materials in medical applications involving permanent implantation in the human body or contact with bodily fluids or tissues, unless the material has been provided from Chemours under a written contract that is consistent with Chemours policy regarding medical applications and expressly acknowledges the contemplated use. For further information, please contact your Chemours representative. For medical emergencies, spills, or other critical situations, call (866) 595-1473 within the United States. For those outside of the United States, call (302) 773-2000.

The information set forth herein is furnished free of charge and based on technical data that Chemours believes to be reliable. It is intended for use by persons having technical skill, at their own discretion and risk. The handling precaution information contained herein is given with the understanding that those using it will satisfy themselves that their particular conditions of use present no health or safety hazards. Because conditions of product use are outside our control, Chemours makes no warranties, express or implied, and assumes no liability in connection with any use of this information. As with any material, evaluation of any compound under end-use conditions prior to specification is essential. Nothing herein is to be taken as a license to operate under or a recommendation to infringe any patents.

NO PART OF THIS MATERIAL MAY BE REPRODUCED, STORED IN A RETRIEVAL SYSTEM OR TRANSMITTED IN ANY FORM OR BY ANY MEANS ELECTRONIC, MECHANICAL, PHOTOCOPYING, RECORDING OR OTHERWISE WITHOUT THE PRIOR WRITTEN PERMISSION OF CHEMOURS.

For more information, visit teflon.com/teflon

For sales and technical support contacts, visit teflon.co/industrialglobalsupport

© 2016 The Chemours Company FC, LLC. Teflon™, Tefzel™ and any associated logos are trademarks or copyrights of The Chemours Company FC, LLC. Chemours™ and the Chemours Logo are trademarks of The Chemours Company.

Replaces: K-27019

C-10187 (3/16)