



Teflon™ PTFE 7C X

Granular Fluoroplastic Resin

Product Information

Description

Teflon™ PTFE 7C X is a white powder with a small particle size. The small particle size of Teflon™ PTFE 7C X helps to minimize voids, even at relatively low molding pressures. Its most unique feature is the irregular, fibrous character of the particles. The fibrous particles promote good capture and uniform distribution of inorganic fillers when they are added to modify the mechanical properties of moldings. It offers an excellent combination of properties that are characteristic of Teflon™ fluoroplastic resins:

- Chemical inertness
- Exceptional dielectric properties
- Heat resistance
- Toughness and flexibility
- Low coefficient of friction
- Non-stick characteristics
- Negligible water absorption
- Excellent weather resistance

Teflon™ PTFE 7C X is preferred for moldings requiring optimum mechanical and electrical properties. Its low bulk density limits the size of moldings from a given mold or press opening. It is often preferred for making filled compounds, especially with metal powders that are difficult to mix because of density differences.

Typical Applications

Many end products are fabricated, which include skived film and sheet. It can be used for applications, such as:

- Gasket
- Bridge or pipeline bearing pads
- Piston rings
- Diaphragms

Many end products are made with filled compounds based on Teflon™ PTFE 7C X. The filled compounds provide a wide choice of modified mechanical properties.

Processing

Teflon™ PTFE 7C X is processed in two steps: preforming and sintering. The powder is first compacted into a preformed shape approximating that of the desired molding. A precise heating (sintering) and cooling cycle is then used to consolidate the molding at temperatures above the crystalline melting point of the neat powder. The properties of a finished molding are dependent on preform pressure, sintering time and temperature, and cooling rate. Teflon™ PTFE 7C X is used to make relatively large objects in molds that can be filled manually. Small particle resins do not flow properly in automatic feeding systems. Refer to the typical property data in Table 1.

Food Contact Compliance

Properly processed products (sintered at high temperatures common to the industry) made from Teflon™ PTFE 7C X resin can qualify for use in contact with food in compliance with FDA 21 CFR 177.1550 and European Regulation (EU) No. 10/2011. For details and information, please contact your Chemours sales representative.

Safety Precautions

Before processing any fluoroplastics, read the Material Safety Data Sheet, available upon request from our Customer Service Group at (844) 773-CHEM/2436 in the U.S. or (302) 773-1000 outside of the U.S. Also read the detailed information in the latest edition of the "Guide to the Safe Handling of Fluoropolymer Resins," published by the Fluoropolymers Division of The Society of the Plastics Industry (www.fluoropolymers.org) or by PlasticsEurope (www.plasticseurope.org).

Storage and Handling

Preforming is easiest when the resin is uniformly between 21–27 °C (70–80 °F). As temperatures decline below this range, the resin will be increasingly difficult to mold without cracks and problems with condensed moisture. Higher temperatures inhibit flow and promote lumping. Storage conditions should be set accordingly. Cleanliness is a critical requirement for successful use of Teflon™ PTFE 7C X. The white resin and high sintering temperatures cause even small foreign particles to become visible in finished moldings. Keep resin drums closed and clean. Good housekeeping and careful handling are essential.

Packaging

Teflon™ PTFE 7C X is packaged in 45-kg (100-lb) drums. Each drum has a bag liner made of polyethylene resin.

Freight Classification

Teflon™ PTFE 7C X, when shipped by rail or express, is classified “Plastics, Synthetic, O.T.L., NOIBN.” Resin shipped by truck is classified “Plastics, Materials Granules.”

Typical Property Data for Teflon™ PTFE 7C X Granular Fluoroplastic Resin

Property	Test Method		Unit	Typical Value
Particle Size, Average Diameter	ISO 13320	ASTM D4894	µm	31
Standard Specific Gravity	ISO 12086	ASTM D4894		2.16
Bulk Density	ISO 12086	ASTM D4894	g/L	260
Tensile Strength ¹	ISO 12086	ASTM D4894	psi (MPa)	5700 (39.3)
Elongation at Break ¹	ISO 12086	ASTM D4894	%	350
Melting Peak				
Initial	ISO 12086	ASTM D4894	°C (°F)	342 ± 10 (647 ± 10)
Second	ISO 12086	ASTM D4894	°C (°F)	327 ± 10 (621 ± 10)
Thermal Instability Index	ISO 12086	ASTM D4894		3.4
Water Content	ISO 12086	ASTM D4894	%	<0.04

Note: Teflon™ PTFE 7C X meets the requirements of ASTM D4894-15, Type II.

Typical properties are not suitable for specification purposes.

¹Measured on skived tapes with a thickness of 0.13 mm.

HOW TO USE THE TEFLON™ BRAND NAME WITH YOUR PRODUCT

Teflon™ is a registered trademark of Chemours for its brand of fluoroplastic resins, coatings, films, and dispersions. The Teflon™ brand name is licensed by Chemours in association with approved applications. Without a trademark license, customers may not identify their product with the Teflon™ brand name, as Chemours does not sell such offerings with the Teflon™ trademark. Unlicensed customers may refer to the Chemours product offering with only the Chemours name and product code number descriptor as Chemours sells its product offerings. There are no fair use rights or exhaustion of rights to use the Teflon™ trademark from buying from Chemours, a Chemours customer, or a distributor without a trademark license from Chemours.

If you are interested in applying for a trademark licensing agreement for the Teflon™ brand, please visit www.teflon.com/license

CAUTION: Do not use Chemours materials in medical applications involving permanent implantation in the human body or contact with bodily fluids or tissues, unless the material has been provided from Chemours under a written contract that is consistent with Chemours policy regarding medical applications and expressly acknowledges the contemplated use. For further information, please contact your Chemours representative. You may also visit www.teflon.com/industrial to download a copy of the “Chemours POLICY Regarding Medical Applications” and “Chemours CAUTION Regarding Medical Applications.” For medical emergencies, spills, or other critical situations, call (866) 595-1473 within the United States. For those outside of the United States, call (302) 773-2000.

The information set forth herein is furnished free of charge and based on technical data that Chemours believes to be reliable. It is intended for use by persons having technical skill, at their own discretion and risk. The handling precaution information contained herein is given with the understanding that those using it will satisfy themselves that their particular conditions of use present no health or safety hazards. Because conditions of product use are outside our control, Chemours makes no warranties, express or implied, and assumes no liability in connection with any use of this information. As with any material, evaluation of any compound under end-use conditions prior to specification is essential. Nothing herein is to be taken as a license to operate under or a recommendation to infringe any patents.

NO PART OF THIS MATERIAL MAY BE REPRODUCED, STORED IN A RETRIEVAL SYSTEM OR TRANSMITTED IN ANY FORM OR BY ANY MEANS ELECTRONIC, MECHANICAL, PHOTOCOPYING, RECORDING OR OTHERWISE WITHOUT THE PRIOR WRITTEN PERMISSION OF CHEMOURS.

For more information, visit teflon.com/industrial

For sales and technical support contacts, visit teflon.com/industrialglobalsupport

© 2015 The Chemours Company FC, LLC. Teflon™ and any associated logos are trademarks or copyrights of The Chemours Company FC, LLC. Chemours™ and the Chemours Logo are trademarks of The Chemours Company.

Replaces: K-26149

C-10123 (11/15)