

# DuPont™ Tedlar®

## polyvinyl fluoride film

### Product Specification

## TGY85SL2

### Physical Properties

Measured Properties	Test Method	Unit	Value
Unit Weight	DuPont Method	$\text{g}\cdot\text{m}^{-2}$	27–30
Gauge Variation	DuPont Method	%	$\leq 20$
Tensile Strength MD/TD	ASTM D882	MPa (ksi)	$\geq 58$ (8.5)
Shrinkage TD @ 130°C	ASTM D1208	%	$\leq 3.0$
Elongation at break MD/TD	ASTM D882	%	$\geq 60$

### Marking and Packaging

<b>Lot Number</b>	Product lot numbers are in the form of YYMMLLNNNN <ul style="list-style-type: none"><li>• YY = Year</li><li>• MM = Month</li><li>• LL = Slitter Identification</li><li>• NNNN = Sequential Number</li></ul>
<b>Label</b>	Product label contains the following information: <ul style="list-style-type: none"><li>• Manufacturer's Name</li><li>• Product Type</li><li>• Width</li><li>• Length</li><li>• Weight</li><li>• Area</li><li>• Lot Number</li></ul>
<b>Packaging</b>	All rolls 610mm (24") width or greater are shipped in suspended packaging.

This specification is current as of the date of publication and is subject to change.



*The miracles of science™*

**For more information, please visit [www.tedlar.com](http://www.tedlar.com)**

Copyright © 2012 DuPont or its affiliates. All rights reserved. The DuPont Oval Logo, DuPont™, The miracles of science™, and Tedlar®, are registered trademarks or trademarks of E. I. du Pont de Nemours and Company or its affiliates.

NO PART OF THIS MATERIAL MAY BE REPRODUCED, STORED IN A RETRIEVAL SYSTEM OR TRANSMITTED IN ANY FORM OR BY ANY MEANS ELECTRONIC, MECHANICAL, PHOTOCOPYING, RECORDING OR OTHERWISE WITHOUT THE PRIOR WRITTEN PERMISSION OF DUPONT.

The information set forth herein is furnished free of charge and is based on technical data that DuPont believes to be reliable. It is intended for use by persons having technical skill, at their own discretion and risk. The handling precaution information contained herein is given with the understanding that those using it will satisfy themselves that their particular conditions of use present no health or safety hazards. Because conditions of product use are outside our control, we make no warranties, express or implied, and assume no liability in connection with any use of this information. As with any material, evaluation of any compound under end-use conditions prior to specification is essential. Nothing herein is to be taken as a license to operate under or a recommendation to infringe any patents.

CAUTION: Do not use in medical applications involving permanent implantation in the human body or contact with internal body fluids or tissues. For other medical applications, see "DuPont Medical Caution Statement," H-50102.

K-26042 10/12



*The miracles of science™*