



# Teflon™ AF Solutions

## Amorphous Fluoropolymer Solutions

### Product Information

Product names may be followed by an X. Products labeled AF 1601 and AF 1601 X are equivalent, as are AF 2400 and AF 2400 X.

#### Description

Teflon™ AF is a family of amorphous fluoropolymers. These materials are similar to other amorphous polymers in optical clarity and mechanical properties, including strength, but also perform like fluoropolymers in their performance over a wide range of temperatures, outstanding electrical properties, and chemical resistance. Teflon™ AF solutions are made of Teflon™ AF amorphous fluoropolymer dissolved in Fluorinert® FC-40.

#### Applications

Teflon™ AF can be used as a low-refractive-index coating or covering for optical devices, including those that must operate over a wide temperature range and in chemically aggressive environments. Teflon™ AF offers a high level of transmission throughout the optical spectrum from infrared through ultraviolet.

In electronics, Teflon™ AF may be used in optoelectronic devices, where its optical clarity, temperature resistance, and dielectric properties are beneficial.

#### Processing

Teflon™ AF 1601 is supplied as a 6% and 18% solution in Fluorinert® FC-40. Teflon™ AF 2400 is supplied as a 1% solution in Fluorinert® FC-40. These solutions can be cast into thin or thick pinhole-free coatings by a variety of techniques, including spinning, spraying, brushing, and dipping.

Whichever coating methods are used, the coated product must be heated above the T<sub>g</sub> (160 °C [320 °F]) or (240 °C [464 °F]) to remove all solvent. This gives a smoother coating and improves the polymer's adherence to the surface. For additional information on adhesion, see the Chemours technical bulletin, "Adhesion Guide for Teflon™ AF"

#### Safety Precautions

WARNING! VAPORS CAN BE LIBERATED THAT MAY BE HAZARDOUS IF INHALED.

Before using Teflon™ AF 1601 or Teflon™ AF 2400, read the Safety Data Sheet and the detailed information in the latest edition of the "Guide to the Safe Handling of Fluoropolymer Resins," published by the Fluoropolymers Division of The Society of the Plastics Industry ([www.plasticsindustry.org](http://www.plasticsindustry.org)) or by PlasticsEurope ([www.plasticseurope.org](http://www.plasticseurope.org)).

#### Handling Practices

Teflon™ AF resins may contain parts per million of residual hexafluoroacetone (HFA). Because HFA hydrates are readily absorbed through the skin, it is necessary to avoid skin contact with the resin during processing. Chemours recommends the use of protective gloves when handling resin during manufacturing operations.

Residual gases (including HF, COF<sub>2</sub>, CO, and HFA) that may be harmful diffuse from Teflon™ AF resins, even at room temperature. To avoid exposure, all resin containers should be opened and used only in well-ventilated areas using local exhaust ventilation (LEV).

#### Packaging and Storage

Developmental quantities of Teflon™ AF 1601 and Teflon™ AF 2400 solutions are packaged in 100 mL sealed glass containers with foamed/carton overpack. Packaging for production quantities will be designed to meet customer needs.

Teflon™ solutions are stable and do not have a shelf life. The solvent Fluorinert® FC-40 is thermally stable and resistant to hydrolysis. The boiling point of the solvent is 160 °C (320 °F). The polymer is thermally stable to very high temperatures and resistant to UV light. Package should be kept tightly closed at all times to prevent contamination from dust particles or other foreign substances.

## Other Information

Products listed on this technical data sheet comply with GB 30981-2020 "Limit of harmful substances in industrial protective coatings", and classified to section 5.1 special functional coatings - polytetrafluoroethylene type coatings which are sintered at a high temperature above 150 °C (chemical resistant, wear resistant, lubricated, non-stick, and other functions) they are exempted from VOC limit requirements.

**Table 1. Typical Property Data for Teflon™ AF Solution Grades**

Property	ASTM Method	Unit	Grade	
			1601	2400
<b>Electrical</b>				
Dielectric Constant	D150		1.93	1.90
Dissipation Factor	D150		0.0001-0.0002	0.0001-0.0003
<b>Optical</b>				
Optical Transmission	D1003	%	>95	>95
Refractive Index	D542		1.31	1.29
<b>Mechanical</b>				
Tensile Strength	D638	MPa		
23 °C (73 °F)			26.9 ± 1.5	26.4 ± 1.9
220 °C (428 °F)			7.7 ± 6.1	4.2 ± 1.8
Elongation at Break, 23 °C (73 °F)	D638	%	17.1 ± 5.0	7.9 ± 2.3
Tensile Modulus	D638	GPa	1.6	1.5
<b>Chemical</b>				
Contact Angle with Water	D570	Degrees	104	105
Critical Surface Energy		Dynes/cm	15.7	15.6
Chemical Resistance—Water Absorption		%	<0.01	<0.01
<b>Other</b>				
Glass Transition Temperature (Tg)	D3418	°C (°F)	160 (320) ± 5	240 (464) ± 10
Specific Gravity	D792		1.78	1.67
Melt Flow Rate (5.0 kg)	D1238	g/10 min	6 ± 4 (at 225 °C [437 °F])	13 ± 4 (at 360 °C [680 °F])
Volume Coefficient of Thermal Expansion	E831	ppm/°C (°F)	260 (500)	301 (572)
Brookfield Viscosity in Fluorinert® FC-40		Pa·sec	0.19–0.22 at 6 wt%	0.09–0.1 at 1 wt%
Solubility in Fluorinert® FC-40 (at room temperature)		%	Up to 18 wt%	Up to 1 wt%

## HOW TO USE THE TEFLON™ BRAND NAME WITH YOUR PRODUCT

Teflon™ is a registered trademark of Chemours for its brand of fluoropolymer resins, coatings, films, and dispersions. The Teflon™ brand name is licensed by Chemours in association with approved applications. Without a trademark license, customers may not identify their product with the Teflon™ brand name, as Chemours does not sell such offerings with the Teflon™ trademark. Unlicensed customers may refer to the Chemours product offering with only the Chemours name and product code number descriptor as Chemours sells its product offerings. There are no fair use rights or exhaustion of rights to use the Teflon™ trademark from buying from Chemours, a Chemours customer, or a distributor without a trademark license from Chemours.

If you are interested in applying for a trademark licensing agreement for the Teflon™ brand, please visit [www.teflon.com/license](http://www.teflon.com/license)

**CAUTION:** Do not use or resell Chemours materials in medical applications involving implantation in the human body or contact with internal bodily fluids or tissues unless agreed to by Seller in a written agreement covering such use. For further information, please contact your Chemours representative. For medical emergencies, spills, or other critical situations, call (866) 595-1473 within the United States. For those outside of the United States, call (302) 773-2000.

The information set forth herein is furnished free of charge and based on technical data that Chemours believes to be reliable. It is intended for use by persons having technical skill, at their own discretion and risk. The handling precaution information contained herein is given with the understanding that those using it will satisfy themselves that their particular conditions of use present no health or safety hazards. Because conditions of product use are outside our control, Chemours makes no warranties, express or implied, and assumes no liability in connection with any use of this information. As with any material, evaluation of any compound under end-use conditions prior to specification is essential. Nothing herein is to be taken as a license to operate under or a recommendation to infringe any patents.

NO PART OF THIS MATERIAL MAY BE REPRODUCED, STORED IN A RETRIEVAL SYSTEM OR TRANSMITTED IN ANY FORM OR BY ANY MEANS ELECTRONIC, MECHANICAL, PHOTOCOPYING, RECORDING OR OTHERWISE WITHOUT THE PRIOR WRITTEN PERMISSION OF CHEMOURS.

For more information, visit [teflon.com/industrial](http://teflon.com/industrial). For sales and technical support contacts, visit [teflon.com/industrialglobalsupport](http://teflon.com/industrialglobalsupport)

© 2021 The Chemours Company FC, LLC. Teflon™ and any associated logos are trademarks or copyrights of The Chemours Company FC, LLC. Chemours™ and the Chemours Logo are trademarks of The Chemours Company.

Fluorinert® is a registered trademark of 3M.

Replaces: K-26989 C-10265 (3/21)