



Teflon™ Powder One Coat/Primer

Industrial Coatings

532-1003

Fact Sheet

532-1003 powder coating is a unique blend of fluoropolymers and other resins, such that each individual particle contains the proper blend of ingredients. 532-1003 has superior toughness, coupled with properties from our tough liquid coatings, excellent corrosion resistance, and good dry lubrication. A major advantage of the powder form is that it has no VOC emissions.

Property Data

Properties ^a	532-1003
Color	Black
Molecular Weight	Low
Melt Flow Rate	High
Coverage, m ² /kg (ft ² /gal) ^b	30 (146)
Particle Size Average, μm ^c	30-48
Bulk Density, g/100 cc	40-60
Density, kg/L (lb/gal)	1.35 (11.27)
Maximum In-Use Temperature, °C (°F)	150 (300) continuous use and 177 (350) intermittent use

^aPhysical constants are averages only and not to be used as product specifications. They may vary up to ±5% of the values shown.

^bTheoretical coverage at dry film thickness (DFT) of 25 μm (1.0 mil) based on 100% application efficiency. It does not take normal production losses into account.

^cParticle size refers to the average particle size measured by laser diffraction.

Application Method

Coating Preparation	Screen powder through 60 mesh (approx. 250 μm) stainless steel or nylon. Insufficient screening can result in application defects.
Application	Use conventional industrial electrostatic powder spray equipment with a voltage between 60-80 kV or enough to maintain particle charge, yet prevent excess film builds. Excessive powder builds may lead to blistering or yield rough films after baking. 532-1003 fluidizes easily and flows smoothly. 532-1003 was not designed for fluidized bed application. However, for a specific kind of part, and with some experimentation, fluidized bed can be a viable technique. Preheat part to 127-150 °C (260-300 °F). Higher temperatures will result in rough films. "Hot flocking" can also be used to apply 532-1003, as long as the part to be coated is sufficiently massive to hold heat. Use of same preheat temperatures as above. Use adequate ventilation.
Recommended DFT*	20-38 μm (0.8-1.0 mil) per coat
Curing (Metal Temp.)	The recommended bake for this product is 10 min at 204 °C (400 °F). At 204 °C (400 °F), the binder is cross-linked. Do not exceed 288 °C (550 °F) bake temperature or film decomposition begins. Staged baking at 150 °C (300 °F) for 10 min, then 204 °C (400 °F) for 10 min has been shown to improve smoothness.
Repair	Use sandpaper to smooth out the imperfection and touch up with a spray of 532-1003 powder. Bake 10 min at 260 °C (400 °F).

*Dry Film Thickness (DFT) measured with Dual probe ED10 or FD10 used in combination with the Dualscope MP20, MP40, FMP20, or FMP40
All recommendations are based upon best knowledge.

Handling and Storage

- Powders should be stored in closed plastic bags.
- Powders may form lumps under prolonged storage; sieving through a coarse screen will restore the powder.
- Shelf life is 18 months at optimal storage conditions: 18–25 °C (65–77 °F). Maximum storage temperature: 30 °C (86 °F).
- Transport conditions: 5–40 °C (40–105 °F). For safe storage conditions, please refer to Safety Data Sheet (SDS).

For medical application and development, consult Chemours.

Food Contact

This product is not approved for food contact applications.

Disposal and Other Considerations

Please follow the guidelines as outlined by The Society of the Plastics Industry (SPI) or Association of Plastics Manufacturers Europe (PlasticsEurope). For detailed information on health and safety, refer to the SDS.

For disposal, please follow these guidelines:

- All treatment, storage, transportation, and disposal of this product and/or container must be in accordance with applicable national and local regulations.
- Do not discharge aqueous dispersions to lakes, streams, or waterways.
- Separate solids from liquid by precipitation and decanting or filtering. Dispose of dry solids in a landfill that is permitted, licensed, or registered to manage industrial solid waste. Discharge liquid filtrate to a wastewater treatment system.
- Incinerate only if incinerator operates at 800 °C (1475 °F) or higher and is capable of scrubbing out hydrogen fluoride and other acidic combustion products.
- Industrial fluoropolymer waste containing additives, such as solvents, primers, or thinners, must be regarded as special waste. Companies should contact their local waste disposal authorities for details of relevant waste disposal regulations.
- Empty containers should preferably be cleaned and recycled. If this is not possible, the containers should be punctured or otherwise destroyed before disposal.

HOW TO USE THE TEFLON™ BRAND NAME WITH YOUR PRODUCT

Teflon™ is a registered trademark of Chemours for its brand of fluoropolymer resins, coatings, films, and dispersions. The Teflon™ brand name is licensed by Chemours in association with approved applications. Without a trademark license, customers may not identify their product with the Teflon™ brand name, as Chemours does not sell such offerings with the Teflon™ trademark. Unlicensed customers may refer to the Chemours product offering with only the Chemours name and product code number descriptor as Chemours sells its product offerings. There are no fair use rights or exhaustion of rights to use the Teflon™ trademark from buying from Chemours, a Chemours customer, or a distributor without a trademark license from Chemours.

If you are interested in applying for a trademark licensing agreement for the Teflon™ brand, please visit www.teflon.com/license

CAUTION: Do not use or resell Chemours materials in medical applications involving implantation in the human body or contact with internal bodily fluids or tissues unless agreed to by Seller in a written agreement covering such use. For further information, please contact your Chemours representative. For medical emergencies, spills, or other critical situations, call (866) 595-1473 within the United States. For those outside of the United States, call (302) 773-2000.

The information set forth herein is furnished free of charge and based on technical data that Chemours believes to be reliable. It is intended for use by persons having technical skill, at their own discretion and risk. The handling precaution information contained herein is given with the understanding that those using it will satisfy themselves that their particular conditions of use present no health or safety hazards. Because conditions of product use are outside our control, Chemours makes no warranties, expressed or implied, and assumes no liability in connection with any use of this information. As with any material, evaluation of any compound under end-use conditions prior to specification is essential. Nothing herein is to be taken as a license to operate under or a recommendation to infringe any patents.

NO PART OF THIS MATERIAL MAY BE REPRODUCED, STORED IN A RETRIEVAL SYSTEM OR TRANSMITTED IN ANY FORM OR BY ANY MEANS ELECTRONIC, MECHANICAL, PHOTOCOPYING, RECORDING OR OTHERWISE WITHOUT THE PRIOR WRITTEN PERMISSION OF CHEMOURS.

For more information, visit teflon.com/industrial

For sales and technical support contacts, visit teflon.com/industrialglobalsupport

The Chemours Company
1007 Market Street
P.O. Box 2047
Wilmington, DE 19899
T: +1 302 773 1000

Asia Pacific
The Chemours Chemical
(Shanghai) Co., Ltd.
Shanghai, China
T: +86 21 3862 2888

Europe
Chemours Belgium BVBA
Kallo, Belgium
T: +32 3 730 2211

Latin America
Chemours do Brasil, S.A.
Sao Paulo, Brasil
T: +55 11 2599 8574

© 2019 The Chemours Company FC, LLC. Teflon™ and any associated logos are trademarks or copyrights of The Chemours Company FC, LLC. Chemours™ and the Chemours Logo are trademarks of The Chemours Company.

C-11778 (2/19)