



Teflon™ ETFE Powder Topcoats

Industrial Coatings

532-6118

Fact Sheet

Ethylene tetrafluoroethylene (ETFE) is a thermoplastic copolymer. This material ETFE 532-6118 is a special filled grade with a very high resistance against water vapour permeation. In an Atlas cell test with boiling water, after 1 year of exposure no blisters, bubbles or delamination could be found, even if only applied in 350µ thickness.

Property Data ¹

Product Code	532-6118
Type	Mid-coat
Colour	Beige
Coverage, ² m ² /kg (ft ² /lb)	22.0 (110)
Particle size, ³ Average, µm	76 – 96
Bulk Density, g/100 cc	55 – 85
Density, kg/l (lbs/gal)	1.778 (14.84)
Maximum In-Use Temperature, °C (°F)	150 (300)

¹Physical constants are averages only and are not to be used as product specifications. They may vary up to ±5% of the values shown

²Theoretical coverage at dry film thickness (DFT) of 1.0 mils (25µ) based on 100% application efficiency. It does not take normal production losses into account

³Particle size refers to the average particle size measured by laser diffraction.

⁴Weight % volatiles based on volatiles with vapor pressure ≥ 0.1 hPa. US VOC (ap) and VOC (le) are listed on the US Safety data sheet, available upon request

Application Method

Coating Preparation	Homogenize powder before opening bag.
Screen	30 mesh (approx. 550 µm) stainless steel or nylon. Insufficient screening can result in application defects.
Application	Use fluidized bed with or without vibration system (depends on powder quantity and particle size of the powder). On flat and/or conductive parts high voltage and higher amperage can be used. On insulated and complex parts amperage should be lowered. In some situations a fixed voltage may be more effective than using an automatic current control setting. The gun settings depend on the gun type and complexity of the part. Recommended general settings: • Product supply: 30%-50% • Air carrier: 3.0 Nm ³ /h • Fluidization bed: 0.3 Nm ³ /h • Electrode fluidization: flat jet 0.2 Nm ³ /h • Amperage: 10 µA • Voltage: 20 kV
Recommended DFT*	Up to 200 µm (8 mil) per coat, total DFT of 650 - 1000 µm (25 - 40 mil)
Recommended Primer	Liquid 699N-129, Powder 532G-6405
Drying (metal temp.)	Powders can be applied dry on wet. Full coating system should be dried before final cure.
Curing (metal temp.)	20-30 minutes at 295-300°C (565-570°F), oven temperature should not be higher than 310°C (590°F).
Multiple coats	Second and subsequent coats can be hot flocked. Terminate by applying a thin layer 532-6210 to get smooth film and avoid any filler to come loose from coating. This last coat may be cured at lower temperature, typically 280°C (535°F)

* Dry Film Thickness (DFT) measured with Dual probe ED10 or FD10 used in combination with the Dualscope MP20, MP40, FMP20 or FMP40

All recommendations are based upon best knowledge

Handling and Storage

- Powders should be stored in closed plastic bags.
- Powders may form lumps under prolonged storage; sieving through a coarse screen will restore the powder
- Powders should be usable for an indefinite period of time without caking or deteriorating if stored at optimal storage conditions: 18°C-27°C (65°F-80°F). Maximum storage temperature 40°C (105°F).
- Transport conditions: 5°C-40°C (40°F-105°F). For safe storage conditions, pls. refer to safety data sheet.

For medical application and development, consult Chemours.

Food Contact

These materials are not intended for use in direct contact with food.

Disposal and Other Considerations

Please follow the guidelines as outlined by [SPI](#) (The Society of the Plastics Industry) or [PlasticsEurope](#) (Association of Plastics Manufacturers Europe). For detailed information on health and safety, refer to the Safety Data Sheet.

For disposal, please follow these guidelines:

- All treatment, storage, transportation, and disposal of this product and/or container must be in accordance with applicable national and local regulations.
- Do not discharge aqueous dispersions to lakes, streams or waterways.
- Separate solids from liquid by precipitation and decanting or filtering. Dispose of dry solids in a landfill that is permitted, licensed or registered to manage industrial solid waste. Discharge liquid filtrate to a wastewater treatment system.
- Incinerate only if incinerator operates at 800°C or higher and is capable of scrubbing out hydrogen fluoride and other acidic combustion products.
- Industrial fluoropolymer waste containing additives such as solvents, primers or thinners must be regarded as special waste. Companies should contact their local waste disposal authorities for details of the relevant waste disposal regulations.
- Empty containers should preferably be cleaned and recycled. If this is not possible, the containers should be punctured or otherwise destroyed before disposal.

For more information on Chemours Nonstick coatings: www.chemours.com or www.teflon.com

The Chemours Company
1007 Market Street
P.O. Box 2047
Wilmington, DE 19899
T: +1 302 773 1000

Asia Pacific
The Chemours Chemical
(Shanghai) Co., Ltd.
Shanghai, China
T: +86 21 3862 2888

Europe
Chemours Belgium BVBA
Kallo, Belgium
T: +32 3 730 2211

Latin America
Chemours do Brasil, S.A.
Sao Paulo, Brasil
T: +55 11 2599 8574

Teflon™ is a trademark of the Chemours Company FC, LLC, only available for use under license.

NO PART OF THIS MATERIAL MAY BE REPRODUCED, STORED IN A RETRIEVAL SYSTEM OR TRANSMITTED IN ANY FORM OR BY ANY MEANS ELECTRONIC, MECHANICAL, PHOTOCOPYING, RECORDING OR OTHERWISE WITHOUT THE PRIOR WRITTEN PERMISSION OF Chemours.

All technical advice, recommendations and services are rendered by Seller free of charge. They are based on technical data which the Seller believes to be reliable, and are intended for use by persons having skill and know-how, at their own discretion and risk. Seller assumes no responsibility for results obtained or damages incurred from their use by Buyer in whole or in part. Such recommendations and technical advice or services are not to be taken as a license to operate under or intended to suggest infringement of any existing patent. All coverage figures are based on 100% application efficiency. These calculations do not take into account normal losses due to production conditions.

CAUTION: Do not use Chemours materials in medical applications involving implantation in the human body or contact with internal body fluids or tissues unless the material has been provided from Chemours under a written contract that is consistent with Chemours policy regarding medical applications and expressly acknowledges the contemplated use. For further information, please contact your Chemours representative. You may also request a copy of the Chemours POLICY Regarding Medical Applications