



Teflon™ Liquid PFA Topcoat

Industrial Coatings

858G-210

Fact Sheet

Teflon™ 858G-210 coating is a water-based PFA topcoat for use on parts which may not be easily powder coated, such as parts with acute angles or parts requiring a thinner coating than a powder coat can provide. The coating has a variety of application uses such as general industrial, food processing and office automation.

Property Data¹

Product Code	Topcoat 858G-210
Color	Clear
Coverage, ² m ² /kg (m ² /L)	6.91 (365)
Viscosity ³ , centipoises	250 - 750
Volume Solids, %	20.8 – 24.8
Weight Solids, %	37.6 – 41.60
Density, kg/l (lbs/gal)	1.29 (10.8)
Maximum In-Use Temperature, °C (°F)	260 (500)
Shipping Class	+140L
Flash Point, SETA closed cup, °C (°F)	None
Food Contact	Yes

¹Physical constants are averages only and are not to be used as product specifications. They may vary up to 5% of the values shown

²Theoretical coverage at dry film thickness (DFT) of 1.0 mils (25µm) based on 100% application efficiency. It does not take normal production losses into account

³Brookfield RVT (Measured with spindle 2 at 20 RPM/25°C)

Application Method:

Substrate	Adhesion to most metals as well as glass, ceramics, etc. that are stable at the baking temperature required.
Surface Preparation	Apply to clean substrate. Any residual oil on the surface will affect the color of the cured film and will adversely affect adhesion.
Mix well before use	Gentle mix 15 minutes. Set the mixer speed so that a vortex is appearing. We recommend the use of an axial flow impeller (for instance a propeller blade impeller). Its size should be 10-12 cm for the 5 kg packaging and 17-20 cm for the 20kg packaging. Typically the rotational speed would be in the range of 50-100 rpm.
Filtering	100 mesh (105µm) stainless steel or nylon.
Typical Spray Gun Settings	Reduced Pressure gun or Conventional or HVLP Nozzle : 1.0-1.4 mm, Air Pressure: 2.0-3.0 bar
Recommended Primer	420G-70X series (8-10µm) on grit blasting; or 850G-314 (8-10 µm) on cleaned smooth surface
Product DFT	0.8–1.2 mil (20–30 µm). Apply over air dried or force dried primer. Total film builds up to 3 mil (75 µm) are possible with multiple coats.
Drying	10 min at 150°C
Curing (metal temperature)	First Coat: 5 or 10 min at 750 °F (400 °C). Subsequent Coats: 15 min at 700 °F (370 °C). Bakes of 800°F will reduce any brownish cast to the coating.
Dilution	Not required
Clean up	Water

* Dry Film Thickness (DFT) measured with Dual probe ED10 or FD10 used in combination with the Dualscope MP20, MP40, FMP20 or FMP40

All recommendations are based upon best knowledge



Handling and Storage

- Gently mix (15 min at 30RPM) before use
- Shelf life is 12 months at optimal storage conditions: 18°C-27°C (65°F-80°F). Maximum storage temperature 40°C (105°F).
- Transport conditions: 5°C-40°C (40°F-105°F). For safe storage conditions, pls. refer to safety data sheet.
- Waterbased product, protect from freezing

For medical application and development, consult Chemours.

Food Contact

This product, when used in combination with another layer compliant with food legislations, is designed to be used in direct contact with food. Applied according to the application method and instructions on this fact sheet, the fully cured system will comply with US FDA food contact regulations.

In the European Union this product complies with:

- Regulation (EC) n° 1935/2004 on materials and articles intended to come into contact with food and is safe to be used and/or sold in accordance with article 3 of this Regulation; and
- Specific national legislations/ recommendations applicable to this category of coatings (non-stick, high temperature resistant) listed in the detailed compliance documentation for food contact applications.

In case this product is not compliant with the specific legal requirements in one EU Member State; This product, in accordance with Article 34-36 of the Treaty on the Functioning of the European Union (TFEU), can still be used and/or sold for food contact applications in all EU Member States, on the basis of its full compliance in at least one Member State of the European Union.

The above is only valid on condition that the product is applied: according to the information outlined in the application method section of this fact sheet, on substrates that are suitable for use in food contact applications, and for EU presuming appropriate processing by the coater/applicator following the Good Manufacturing Practices Regulation (EC) n°2023/2006 /EC.

Any changes or variations from application method indicated in this fact sheet for food contact applications shall be assessed prior to its use.

For detailed regulatory compliance information and/or any potential regulatory restrictions on the use of this (primer, midcoat, topcoat) product within one of the corresponding Industrial Finishes coating systems from Chemours, we refer you to the US FDA and/or EU compliance documentation from Chemours for the specific coating system utilizing this product, as well as the technical advice included in this product factsheet.

For details and information please contact your Chemours representative.

Disposal and Other Considerations

Please follow the guidelines as outlined by [SPI](#) (The Society of the Plastics Industry) or [PlasticsEurope](#) (Association of Plastics Manufacturers Europe). For detailed information on health and safety, refer to the Safety Data Sheet.

For disposal, please follow these guidelines:

- All treatment, storage, transportation, and disposal of this product and/or container must be in accordance with applicable national and local regulations.
- Do not discharge aqueous dispersions to lakes, streams or waterways.
- Separate solids from liquid by precipitation and decanting or filtering. Dispose of dry solids in a landfill that is permitted, licensed or registered to manage industrial solid waste. Discharge liquid filtrate to a wastewater treatment system.
- Incinerate only if incinerator operates at 800°C or higher and is capable of scrubbing out hydrogen fluoride and other acidic combustion products.
- Industrial fluoropolymer waste containing additives such as solvents, primers or thinners must be regarded as special waste. Companies should contact their local waste disposal authorities for details of the relevant waste disposal regulations.
- Empty containers should preferably be cleaned and recycled. If this is not possible, the containers should be punctured or otherwise destroyed before disposal.

For more information on Chemours Nonstick coatings: www.chemours.com or www.teflon.com

The Chemours Company
1007 Market Street
P.O. Box 2047
Wilmington, DE 19899
T: +1 302 773 1000

Asia Pacific
The Chemours Chemical
(Shanghai) Co., Ltd.
Shanghai, China
T: +86 21 3862 2888

Europe
Chemours Belgium BVBA
Kallo, Belgium
T: +32 3 730 2211

Latin America
Chemours do Brasil, S.A.
Sao Paulo, Brasil
T: +55 11 2599 8574

Teflon™ is a trademark of the Chemours Company FC, LLC, only available for use under license.

NO PART OF THIS MATERIAL MAY BE REPRODUCED, STORED IN A RETRIEVAL SYSTEM OR TRANSMITTED IN ANY FORM OR BY ANY MEANS ELECTRONIC, MECHANICAL, PHOTOCOPYING, RECORDING OR OTHERWISE WITHOUT THE PRIOR WRITTEN PERMISSION OF Chemours.

All technical advice, recommendations and services are rendered by Seller free of charge. They are based on technical data which the Seller believes to be reliable, and are intended for use by persons having skill and know-how, at their own discretion and risk. Seller assumes no responsibility for results obtained or damages incurred from their use by Buyer in whole or in part. Such recommendations and technical advice or services are not to be taken as a license to operate under or intended to suggest infringement of any existing patent. All coverage figures are based on 100% application efficiency. These calculations do not take into account normal losses due to production conditions.

CAUTION: Do not use Chemours materials in medical applications involving implantation in the human body or contact with internal body fluids or tissues unless the material has been provided from Chemours under a written contract that is consistent with Chemours policy regarding medical applications and expressly acknowledges the contemplated use. For further information, please contact your Chemours representative. You may also request a copy of the Chemours POLICY Regarding Medical Applications